



# Santa Fe Spanish Texture

Product Data Sheet

## Description:

Santa Fe Spanish Texture is a proprietary mixture of Portland Cement, hydrated lime, silica sand and proprietary additives.

## Uses:

Santa Fe Spanish Texture is a Premium ready-mixed material that will achieve most textures (skip, lace, Monterrey weave, cat's face, etc.). Santa Fe Spanish Texture can also be used to achieve a smooth texture with the use of UltraKote Ultra-Bond.

## Color:

Natural Gray  
White (special order only)

## Packaging:

80 lb. (36.29 Kg) paper sack

## Mixing:

To begin, place 1 to 1.5 gallons of potable water into a mechanical mixer. As the mixer is running add one 80 lb. bag of Santa Fe Spanish Texture. Gradually add the remaining .5 to 1 gallons of potable water and blend until the desired consistency is achieved (about 4 to 5 minutes). Stop the mixing and allow the material to slake for 3 to 4 minutes. Then start the mixing again to break the initial set (usually 1 to 2 minutes). Working time per batch is 45 minutes or less. **NOTE:** *The amount of water needed to reach the desired workability will vary with temperature, humidity, wind,*

*exposure, and site location or region.*

## Coverage :

Coverage will vary depending on the desired texture and on temperature conditions and substrate.

## Limitations:

Santa Fe Spanish Texture should be applied when surface and ambient temperatures are between 38° F (3.33°C) and 110° F (43.33°C) during application and cure time. Santa Fe Spanish Texture is not recommended for use over painted surfaces or stucco accessories. Weather conditions will effect drying time and workability.

## Surface Preparation:

Surface must be clean and free of bond-inhibiting materials such as dirt, dust, rust, grease, oil, efflorescence, mildew, fungus, form-release agents, or any other contaminants. Remove and repair any loose mortar, stucco, concrete, or masonry by water blasting, sand blasting, scraping, or using a wire brush. Repair all cracks with a patching compound and prime the entire surface prior to application to avoid telegraphing lines through the dried finish.

## Application:

Santa Fe Spanish Texture should be applied 2 to 3 days after the initial application of Santa Fe Base, UltraKote one coat, or the

second coat of UltraKote Traditional Stucco Cement. Santa Fe Spanish Texture must not exceed a thickness of 3/8" in one application. Always work to a wet edge to avoid cold joints.

## Curing/Drying:

Santa Fe Spanish Texture must be kept moist for at least 48 hours. Start light fogging after the initial set (1 to 2 hours). Finish should cure completely within 28 days.

## Shelf Life:

One year when stored in a cool dry location out of direct sunlight and kept from freezing.

## Clean Up:

Clean tools and equipment with water immediately after use.

## UltraKote Products, Inc.

327 S. 27th Avenue  
Phoenix, AZ 85009  
Phone: (602) 272-5830 • (800) 224-2344

Last Revised : March 2006

# Santa Fe Spanish Texture

## Product Data Sheet

---

**Precautions:**

KEEP OUT OF THE REACH OF CHILDREN. Not for internal consumption. Do not apply in non-ventilated area. Use protective equipment such as gloves, eye protection and clothing.

**First Aid:**

In case of eye contact, flush with water at least 15 minutes. In case of skin contact, wash affected areas with soap and water. If irritation persists, SEEK MEDICAL ATTENTION. Remove and wash contaminated clothing. If inhalation causes physical discomfort, remove to fresh air. If discomfort continues or any breathing difficulty occurs or if swallowed, SEEK IMMEDIATE MEDICAL ATTENTION. For additional information refer to the Santa Fe Spanish Texture Material Safety Data Sheet (MSDS).

**Disposal:**

Dispose of in accordance with local, state or federal regulations.

**Warning:**

KEEP OUT OF REACH OF CHILDREN. NOT FOR INTERNAL CONSUMPTION, FOR INDUSTRIAL USE

**Spills:**

Scrape up and wash with water immediately. If material has set, scrape material with appropriate tools and clean with citric acid.

**Prop 65:**

This product contains materials listed by the state of California as known to cause cancer, birth defects, or other reproductive harm.

**Technical Support:**

For technical support call 1-602-272-5830. Information contained in this Product Data Sheet conforms to the standard detail recommendations and specifications for the installations of UltraKote products as of the date published on this document. UltraKote Products, Inc. assumes no liability, expressed or implied, as to the architecture, engineering or workmanship of any project. To insure that you are using the latest, most current information, contact UltraKote Products, Inc

---