

sand finish

Cement Texture available in #16 sand and #20 sand



ULTRAKOTE SAND FINISH is a proprietary mixture of Portland Cement, hydrated lime, silica and / or marble sand and proprietary additives. Sand Finish is available in #16 and #20 sand size.

Uses:

Ultrakote Sand Finish is a premium ready-mixed finish texture material for use over Ultrakote 1 or Ultrakote pre-mix. Paint follows the Sand Finish texture application.

Features:

- Factory blended
- Applicator friendly

Benefits:

- Consistent quality from bag to bag
- Easy to trowel and easy to float

Surface Preparation:

Surface must be clean and free of bond-inhibiting materials such as dirt, dust, rust, grease, oil, efflorescence, mildew, fungus, form-release agents or any other contaminants. Remove and repair any loose paint, mortar, stucco, concrete or masonry by water blasting, sand blasting, scraping or using a wire brush. Repair all cracks with patching compound and prime the entire surface prior to application to avoid telegraphing lines through the dried finish.

ultrakote[™]
by  **cemix**

Product Specifications:

Packaging:

90 lbs (40.9 kg) paper bag

Coverage:

Approximate coverage are as follows:

35 ft² using #16 grit sand
40 ft² using #20 grit sand

Coverage will vary depending on temperature conditions and substrate.

Color:

Natural Grey

Clean up:

Clean tools and equipment with water immediately after use.

Shelf Life:

1 year when stores in a cool dry location out of direct sunlight and kept from freezing.

sand finish



Cement Texture available in #16 sand and #20 sand

Mixing:

To begin, place 1 to 1.5 gallons of potable water into a mechanical mixer. As the mixer is running add one 90 lb bag of Sand Finish. Gradually add the remaining .5 to 1 gallons of potable water and blend until the desired consistency is achieved (about 4 to 5 minutes). Stop the mixing and allow the material to slake for 3 to 4 minutes. Then start the mixing again to break the initial set (usually 1 to 2 minutes). Working time per batch is 45 minutes or less. NOTE: The amount of water needed to reach the desired workability will vary with temperature, humidity, wind, exposure and site location or region.

Application:

Sand Finish should be applied 2 to 3 days after the initial application of Ultrakote 1 or Ultrakote pre-mix, Ultrakote One Coat or the second coat of Ultrakote Traditional Stucco Cement. Sand Finish must not exceed a thickness of 3/8" in one application. Always work to a wet edge to avoid cold joints.

Curing / Drying:

Sand Finish must be kept moist for at least 48 hours. Start light fogging after the initial set (1 to 2 hours). Finish should cure completely within 28 days.

Limitations:

Sand Finish should be applied when surface and ambient temperatures are between 38°F (3.33°C) and 110°F (43.33°C) during application and cure time. Sand Finish is not recommended for use over painted surfaces or stucco accessories. Weather conditions will affect drying time and workability.

Precaution:

KEEP OUT OF THE REACH OF CHILDREN.

Not for internal consumption.

Do not apply in non-ventilated areas.

Use protective equipment such as gloves, eye protection and clothing.

First Aid:

In case of eye contact, flush with water at least 15 minutes.

In case of skin contact, wash affected areas with soap and water.

If irritation persists, SEEK MEDICAL ATTENTION.

Remove and wash contaminated clothing.

If inhalation causes physical discomfort, remove to fresh air.

If discomfort continues, any breathing difficulty occurs or if swallowed, SEEK MEDICAL ATTENTION.

For additional information refer to the material Safety Data Sheet (MSDS).

Disposal:

Dispose of in accordance with local, state or federal regulations.

Warning:

KEEP OUT OF THE REACH OF CHILDREN.

NOT FOR INTERNAL CONSUMPTION, FOR INDUSTRIAL USE ONLY.

Spills:

Scrape up and wash with water immediately. If material has set, scrape material with appropriate tools and clean with citric acid.

Prop 65:

This product contains material listed by the state of California known to cause cancer, birth defects or other reproductive harm.

Technical support:

For technical support call 1-602-272-5830. Information contained in this product Information Guide conforms to the standard detail recommendations and specifications for the installations of Ultrakote Products as of the date published on this document. Ultrakote Products, Inc. assumes no liability, expressed or implied, as to architecture, engineering or workmanship of any project. To insure that you are using the latest, most current information, contact Ultrakote Products, Inc. or visit website at: www.ultrakoteproducts.com